

# DuraSurf™ ASC-UV

Crown Plastics **DuraSurf™ ASC-UV** is an anti-static/conductive UV-stable UHMW-PE blend. Possessing the highest level of conductivity in the industry (with a surface resistivity of  $10^2 - 10^3$ ), **DuraSurf™ ASC-UV** protects against static build up that occurs in powder conveying and dust collection and provides discharge protection in electronics, appliances, mail sorting equipment, copiers, printers and computers.

Specifically designed to meet the rigors and harsh environments of the outdoors, **DuraSurf™ ASC-UV** has the highest UV stability in the industry, lasting up to 10 times longer in the outdoors than standard UHMW products.

**DuraSurf™ ASC-UV** is available in wear strips or with adhesive backing. A wide range of adhesives is available to meet virtually any application.



## AVAILABLE THICKNESS

.031" (.78 mm), .040" (1.02 mm), .062" (1.57 mm), .080" (2 mm), .093" (2.36 mm), .125" (3.17 mm)

## AVAILABLE WIDTHS

All dimensions between 1/4" (6.35 mm) and 24" (610 mm)

## UHMW PROPERTIES

- Excellent abrasion and wear resistance
- Very high impact strength
- No moisture absorption
- Self-lubricating – no need for oils or lubricants
- Excellent noise abatement properties
- Chemical resistance and corrosion resistant
- Maintains performance and properties at -30°C
- Meets ASTM-D-4020
- Conforms to flammability rating UL 94 HB

# DuraSurf™ ASC-UV

by CROWN PLASTICS

MECHANICAL PROPERTIES	ASTM Test	Units Metric (U.S.)	UHMW Thickness Gauges		
			.031"	.062"	.125"
Density	D792	gm/cc	0.93	0.93	0.93
Tensile Strength @ Yield	D638	MPa(psi)	23(3300)	20(2964)	22(3227)
Tensile Strength @ Break	D638	MPa(psi)	53(7740)	49(7056)	44(6373)
Elongation @ Break	D638	%	60	463	466
Youngs "E" Modulus	D638	MPa(psi x 105)	725(1.05)	731(1.06)	672(.097)
Izod Impact Strength	D256 <sup>(1)</sup>	J/m(ft-lb/in notch)	*	*	80(16.8)
Hardness Shore "D"	D2240	-	65	65	65
Water Absorbtion	D570	%	Nil	Nil	Nil
Rel. Solution Viscosity	D4020	dl/gm	2.3-3.5	2.3-3.5	2.3-3.5
Coefficient of Friction	D1894-96	Static	.16	.16	.16
Coefficient of Friction	D1894-96	Dynamic	.14	.13	.14

(1) Izod Impact: Samples have 2(15° +/- 1/2°) notches on opposite sides to a depth of 5mm

THERMAL PROPERTIES	ASTM Test	Units Metric (U.S.)	UHMW Thickness Gauges		
			.031"	.062"	.125"
Crystalline Melting Range	Polarizing	°C(°F)	136(276)	134(273)	134(273)
Crystallinity	D3417-96	%	48	47	50
Coefficient of Linear Expansion					
20° to 100° C	D696	K <sup>-1</sup>	*	*	1.5 x 10 <sup>-4</sup>
-20° to -100° C	D696	K <sup>-1</sup>	*	*	9.18 x 10 <sup>-5</sup>

ELECTRICAL PROPERTIES (For Conductive Black Only)	ASTM Test	Units Metric (U.S.)	UHMW Thickness Gauges		
			.031"	.062"	.125"
Volume Resistivity	D257	Ohms/cm	5.9544x10 <sup>7</sup>	1.4516x10 <sup>7</sup>	>2x10 <sup>7</sup>
Dielectric Strength	D150	Kv/cm(V/mil)	*	*	142
Dielectric Constant	D150		2.481	2.454	2.542
Surface Resistivity	D257	Ohms	10 <sup>3</sup>	10 <sup>3</sup>	10 <sup>3</sup>
Static Decay		Seconds	<.01	<.01	<.01
Dissipation Factor					
At 50Hz	D150		0.0594	0.0213	0.0082
At 10KHz	D150		0.1085	0.0690	0.0022
At 5MHz	D150		0.1035	0.2340	0.0034

## Comparison of Dynamic Coefficient of Friction on Polished Steel

Material	UHMW-PE	Nylon 6	Nylon 6/6	Nylon MoS2	PTFE	Acetal Polymer
Dry	.10 – .22	.15 – .40	.15 – .40	.12 – .20	.04 – .25	.15 – .35
Water	.05 – .10	.14 – .19	.14 – .19	.10 – .12	.04 – .08	.04 – .20
Oil	.05 – .08	.02 – .11	.02 – .11	.08 – .10	.04 – .05	.05 – .08

\* No reading could be taken due to material thickness



ADVANCED THERMOPLASTIC SOLUTIONS

Crown Plastics Co., Inc.  
 116 May Drive • Harrison, Ohio 45030 U.S.A.  
 800-368-0238 • www.CrownPlastics.com  
 International Calling: 00-1-513-367-0238  
 sales\_information@crowncplastics.com  
 In Europe: sales-europe@crowncplastics.com