

Coefficient of Friction - Baseline = Galvanized Steel

Substrate	Coefficient	Difference	% Improvement
Galvanized	0.557	0	0%
Mild Steel	0.423	0.134	24%
UHMW	0.369	0.188	34%
STS	0.283	0.274	49%

Methodology: Static friction at varying angles of response